

# NOVEL ASPECTS IN DISLOCATION CONTINUUM THEORY: J-, M-, AND L-INTEGRALS

E. Agiasofitou\*, and M. Lazar

*Darmstadt University of Technology, Department of Physics*

*Hohschulstr. 6, 64289, Darmstadt, Germany*

*e-mail: agiasofitou@mechanik.tu-darmstadt.de*

## 1. Introduction

In this work, new aspects in dislocation continuum theory concerning the **J**-, **M**-, and **L**-integrals are presented within the framework of three-dimensional, linear, incompatible elasticity theory. First, the **J**-, **M**-, and **L**-integrals are derived for two straight (edge and screw) dislocations and second for a single (edge and screw) dislocation in isotropic materials. The results provide to the **J**-, **M**-, and **L**-integrals an important physical interpretation revealing their significance in dislocation continuum theory.

## 2. J-, M-, and $L_3$ -integrals of straight dislocations

For two parallel edge dislocations with Burgers vectors in  $x$ -direction, the **J**-, **M**-, and  $L_3$ -integrals per unit dislocation length are given by [1]

$$(1) \quad \frac{J_1}{l_z} = 2K_{xx}^e \frac{\cos \varphi \cos 2\varphi}{\bar{r}},$$

$$(2) \quad \frac{J_2}{l_z} = 2K_{xx}^e \frac{\sin \varphi (2 + \cos 2\varphi)}{\bar{r}},$$

$$(3) \quad \frac{M}{l_z} = K_{xx}^e \left[ 2 - \ln \frac{\bar{r}}{L} - \sin^2 \varphi \right],$$

$$(4) \quad \frac{L_3}{l_z} = K_{xx}^e \sin 2\varphi,$$

where

$$(5) \quad K_{xx}^e(b_x, b'_x) = \frac{\mu b_x b'_x}{4\pi(1-\nu)}$$

is the *pre-logarithmic energy factor* for edge dislocations with Burgers vectors in  $x$ -direction. Here,  $\mu$  is the shear modulus,  $\nu$  is the Poisson ratio,  $L$  is the size of the dislocated body (or outer cut-off radius),  $\bar{r} = \sqrt{\bar{x}^2 + \bar{y}^2}$  is the distance between the two dislocations, and  $\varphi$  is the location angle of the dislocation with Burgers vector  $\mathbf{b}$ .

The **M**-integral between two edge dislocations with Burgers vectors in  $x$ -direction can be written in terms of the corresponding interaction energy as follows

$$(6) \quad \frac{M}{l_z} = 2K_{xx}^e + \frac{1}{2} \frac{U_{\text{int}}}{l_z},$$

where

$$(7) \quad \frac{U_{\text{int}}}{l_z} = -2K_{xx}^e \left[ \ln \frac{\bar{r}}{L} + \sin^2 \varphi \right].$$

Eq. (6) states that the *M*-integral of two parallel edge dislocations with Burgers vectors in  $x$ -direction per unit

dislocation length is half the interaction energy between the two dislocations per unit length, plus twice the pre-logarithmic energy factor  $K_{xx}^e$ .

Important results are summarized as follows:

- The **J**-integral of dislocations is the Peach-Koehler force (interaction force) between two dislocations.
- Eq. (6) provides to the **M**-integral the physical interpretation of the interaction energy between the two straight dislocations.
- The configurational work produced by the Peach-Koehler force for straight dislocations (per unit dislocation length) is constant, and equals twice the corresponding pre-logarithmic energy factor.
- The  $L_3$ -integral of two straight dislocations is the  $z$ -component of the configurational vector moment or the rotational moment (torque) about the  $z$ -axis caused by the interaction of the two dislocations.
- Fundamental relations between the **J**-,  $L_3$ -, and **M**-integrals of straight dislocations have been found and they show that the **J**-,  $L_3$ -, and **M**-integrals are not independent. If the **M**-integral is given, then the  $J_1$ -,  $J_2$ -,  $J_r$ -,  $J_\varphi$ -, and  $L_3$ -integrals can be easily calculated from it. From that point of view, the **M**-integral is of primary importance.
- The translational energy-release  $\mathcal{G}_k^T$  of straight dislocations is identical to the  $J_k$ -integral.
- The rotational energy-release  $\mathcal{G}^R$  of straight dislocations equals twice the value of the  $L_3$ -integral.

### 3. **J**-, **M**-, and $L_3$ -integrals of a single dislocation

For a single edge dislocation with Burgers vector  $b_x$ , the **J**-, **M**-, and  $L_3$ -integrals per unit dislocation length, are given respectively [2]

$$(8) \quad \frac{J_1}{l_z} = 2K_{xx}^e \frac{1}{\epsilon}, \quad \frac{J_2}{l_z} = 0,$$

$$(9) \quad \frac{M}{l_z} = K_{xx}^e \left[ \ln \frac{L}{\epsilon} + 2 \right], \quad \frac{L_3}{l_z} = 0,$$

where

$$(10) \quad K_{xx}^e(b_x) = \frac{\mu b_x^2}{4\pi(1-\nu)}$$

is the *pre-logarithmic energy factor* for a single edge dislocation with Burgers vector in  $x$ -direction. Here,  $\epsilon$  is the inner cut-off radius being proportional to the constant dislocation core radius.

An important outcome is that the **M**-integral (per unit length) of a single dislocation represents the total energy  $U_{\text{total}}$  of the dislocation (per unit length) which consists of the self-energy (per unit length) plus the dislocation core energy (per unit length)

$$(11) \quad M/l_z = U_s/l_z + U_{\text{core}}/l_z = U_{\text{total}}/l_z.$$

The dislocation core energy can be identified with the work done by the Peach-Koehler force. It is shown that the dislocation core energy (per unit length) is twice the corresponding pre-logarithmic energy factor.

### References

- [1] E. Agiasofitou and M. Lazar. Micromechanics of dislocations in solids: **J**-, **M**-, and **L**-integrals and their fundamental relations, *Int. J. Eng. Sci.*, 114, 16-40, 2017.
- [2] M. Lazar and E. Agiasofitou. Eshelbian dislocation mechanics: **J**-, **M**-, and **L**-integrals of straight dislocations, *Mech. Res. Commun. (Special Issue G.A. Maugin)*, <http://dx.doi.org/10.1016/j.mechrescomm.2017.09.001>, 2017.